

STRESS AND EFFICIENCY STUDIES IN EDGE-DEFINED
FILM-FED GROWTH

MOBIL SOLAR ENERGY CORPORATION

J. Kalejs

TECHNOLOGY ADVANCED MATERIALS RESEARCH TASK	REPORT DATE APRIL 30, 1986
APPROACH STRESS AND EFFICIENCY STUDIES IN EFG CONTRACTOR MOBIL SOLAR ENERGY CORPORATION, CONTRACT NUMBER 956312	STATUS: <ul style="list-style-type: none"> ● STRESS ANALYSIS SHOWS POTENTIAL FOR REDUCING SHEET STRESS AT LOWER GROWTH SPEEDS (< 2 CM/MIN FOR EFG) EXISTS: <ul style="list-style-type: none"> - WHEN SHEET EDGES ARE COOLER THAN CENTERLINE. - REDUCTIONS SENSITIVE TO CREEP BELOW 1200°C. ● QUANTITATIVE RELATIONSHIPS ESTABLISHED BETWEEN L AND N_d FOR FZ SILICON STRESSED ABOVE 900°C: <ul style="list-style-type: none"> - $L \sim N_d^{-1/4}$. - POINT DEFECT CONTRIBUTIONS TO DEGRADATION DEFINED. ● DOPANTS IN EFG MATERIAL SHOWN TO INFLUENCE DISLOCATION ACTIVITY, POINT DEFECT RECOMBINATION.
GOALS <ul style="list-style-type: none"> ● TO DEFINE MINIMUM STRESS CONFIGURATION FOR SILICON SHEET GROWTH. ● TO QUANTIFY DISLOCATION ELECTRICAL ACTIVITY AND LIMITS ON CELL EFFICIENCY. ● TO STUDY BULK LIFETIME DEGRADATION DUE TO INCREASE IN DOPING LEVELS. 	

Topics of Presentation

- BRIEF SUMMARY OF WORK 1982-86.
- DEVELOPMENTS SINCE 25TH PIM.

ADVANCED SILICON SHEET

Stress Studies, 1982-1986: Accomplishments

- DEVELOPED FINITE ELEMENT ANALYSIS FOR CALCULATING RESIDUAL STRESS WITH PLASTIC DEFORMATION IN HIGH SPEED SHEET GROWTH (WITH PROF. J. HUTCHINSON, HARVARD U.).
- VERIFIED QUANTITATIVE FINITE ELEMENT MODEL FOR EFG CONTROL VARIABLE RELATIONSHIPS/TEMPERATURE PROFILE CALCULATIONS (WITH PROF. R.A. BROWN, MIT).
- DEVELOPED RESIDUAL STRESS MEASUREMENT TECHNIQUE FOR EFG MATERIAL USING SHADOW MOIRE INTERFEROMETRY (WITH PROF. S. DANYLUK, U. OF ILLINOIS AT CHICAGO).
- TRANSIENT CREEP INVESTIGATED IN SILICON FOR 800-1400°C IN STRAIN (10^{-5}) AND STRAIN RATE (10^{-4} s^{-1}) REGIMES OF SHEET GROWTH.

Defect Electrical Activity Studies, 1984-1986: Accomplishments



- DEVELOPED QUANTITATIVE MINORITY CARRIER DIFFUSION LENGTH MEASUREMENTS FOR DISLOCATED, INHOMOGENEOUS MATERIAL USING EBIC.
- OBTAINED QUANTITATIVE DATA ON DOPANT (B, GA) INFLUENCE ON DEFECT DENSITIES AND ELECTRICAL ACTIVITY IN EFG MATERIAL.

Dislocation Electrical Activity

- L vs. N_d RELATIONSHIPS ESTABLISHED FOR FZ SILICON STRESSED IN TEMPERATURE RANGE 900-1400°C
 - MICRODEFECT RECOMBINATION LIMITS IN $N_d \leq 10^4 \text{ cm}^{-2}$ REGIONS.
 - DISLOCATION EFFECTS GIVE $L \sim N_d^{-1/4}$ ABOVE N_d THRESHOLD THAT DEPENDS ON MICRODEFECT RECOMBINATION LEVEL.
- CONTRAST TO AS-GROWN DISLOCATION ACTIVITY FOR WHICH $L \sim N_d^{-1/2}$ ($\tau \sim N_d^{-1}$).

ADVANCED SILICON SHEET


Diffusion Length Dependence on Heat Treatment and Dislocation Density



ORIGINAL PAGE IS
 OF POOR QUALITY


ADVANCED SILICON SHEET

EBIC Line Scans of Dislocations in High and Low Resistivity
EFG Silicon Ribbon



ADVANCED SILICON SHEET

ORIGINAL PAGE IS
OF POOR QUALITY



Dislocation Versus Point Defect Limitations on Lifetime

- RESULTS SUGGEST ELECTRICAL ACTIVITY OF GROWN-IN DISLOCATIONS DIFFERS FROM CREEP-RELATED DISLOCATIONS.
- $L \sim N_d^{-1/4}$ ($\tau \sim N_d^{-1/2}$); DEPENDENCE MAY BE RELATED TO DISLOCATION "DEBRIS" OR TOTAL AREA SWEEPED OUT BY DISLOCATIONS, REQUIRES POINT DEFECT-DISLOCATION INTERACTION DYNAMICS TO BE INCLUDED.
- L IS NOT EQUAL TO MEAN DISLOCATION SEPARATION $\ell = N_d^{-1/2}$ FOR ANY SITUATION, INDICATING ONLY SMALL FRACTION OF CORE SITES ARE ACTIVE.

ADVANCED SILICON SHEET

Future Directions for Electrical Activity Studies

DEVELOPMENT OF PASSIVATION SCHEMES FOR DEFECTS AND
PROCESSING/PASSIVATION OPTIMIZATION CRUCIAL TO
VIABILITY OF CURRENT SHEET MATERIAL FOR LOW-COST
PHOTOVOLTAIC INDUSTRY.

CURRENT EFG STATUS:

L: 100-200 MICRONS
 η : 13-15% (45 cm² AREAS)



FUTURE REQUIREMENTS:



L: 200-300 MICRONS
 η : $\geq 16\%$

FUNDAMENTAL NEED IS FOR DEVELOPMENT OF MODELS FOR
AND IDENTIFICATION OF RELATIVE CONTRIBUTIONS OF
POINT DEFECTS AND DISLOCATIONS TO LIFETIME
LIMITATIONS, PARTICULARLY IN LOW RESISTIVITY SILICON.


- FINITE ELEMENT MODELING OF EFFECTS OF TRANSVERSE ISOTHERM
NONUNIFORMITY ON STRESS
 - P. MATAGA, J. HUTCHINSON (HARVARD U.).
- STRESS REDISTRIBUTION IN FINITE SIZE BLANKS
 - L. BUCCIARELLI (MIT).
- STRESS RELAXATION MEASUREMENT IN SILICON BETWEEN
800°C AND 1200°C
 - PLANS FOR EXPERIMENTS.

ADVANCED SILICON SHEET






ADVANCED SILICON SHEET



Transverse Isotherm Effects: Conclusions

- NONUNIFORMITY LEADS TO HIGHER MAXIMUM STRESS IN THE SHEET
 - INCREASES TENDENCY FOR BUCKLING.
 - INCREASES DEFECT DENSITY.
 - ONLY EDGE COOLING REDUCES RESIDUAL STRESS.
- SIGNIFICANT COMPENSATION FOR HIGH AXIAL TEMPERATURE PROFILE NONUNIFORMITY CANNOT BE PRODUCED FOR MODERATE (100-300°C) EDGE COOLING.
- RESIDUAL STRESS DISTRIBUTION IS FUNDAMENTALLY ALTERED
 - POSSIBLE THERE ARE TEMPERATURE DISTRIBUTIONS WHICH REDUCE STRESS TO ZERO.
 - CREEP BEHAVIOR BETWEEN 800°C AND 1200°C NEEDS TO BE STUDIED.


Coordination of Frame and Stress Components Sign Convention



ADVANCED SILICON SHEET


Residual Stress Distribution in Semi-Infinite Ribbon

Note $y=0$. is ribbon center line
 Note σ_{xx} is plotted; other stress components are zero.




Stress Component Variation with "x" at $y = 0.0$

Note: Half length of ribbon $L = 4 \times$ (the half width)
 Note: For x negative:
 σ_{xx} is symmetrical
 σ_{yy} is symmetrical
 σ_{xy} is a-symmetrical



ADVANCED SILICON SHEET

Stress Component Variation with "x" at $y = 0.5$



Stress Redistribution in Finite Size Blanks: Summary

- METHOD FOR CALCULATING SHEAR FLOW DEVELOPED
 - CAN BE OBTAINED FOR ANY SIZE BLANK.
 - CAN BE RELATED TO GROWN-IN THERMOELASTIC STRESS IN SEMI-INFINITE SHEET.
- SIGNIFICANT STRESS REDISTRIBUTION AT BLANK END PRODUCES LARGE TENSILE NON-ZERO σ_{YY} COMPONENT.

Stress Relaxation Measurements in Silicon ($800^{\circ}\text{C} - 1200^{\circ}\text{C}$)

- PREVIOUS CREEP MEASUREMENTS OBTAIN

$$\frac{\partial \epsilon}{\partial T}, \sigma \text{ CONSTANT}$$

$$\text{CONSTITUTIVE LAW: } \dot{\epsilon} \sim F(T) \sigma^N$$

- RELAXATION MEASUREMENTS WILL OBTAIN

$$\frac{\partial \sigma}{\partial T}, \epsilon \text{ CONSTANT}$$